



Technical Data Sheet
ELKALUB GLS 569
Assembly paste for ink boxes

Appaearence	:	white, solid	
Chemical Composition	:	Perfluoropolyether, organic thickener, inorganic thickener	
Resistance	:	resistant against inks and varnishes in printing industry as well as against washing water selected by manroland	
Dropping point in °C	:	> 180°C	DIN ISO 2176
Base oil viscoisty	:	380 mm ² /s at 40°C	
Unworked penetration	:	155 ±15	DIN 51 804

These data were issued according to samplings and multiple deliveries to manroland. Any modifications will only be effected on the initiative of manroland.

Vöhringen, 01.02.2012 / JB